



Hypax 1409 BBS

Corrosion Preventive Liquid

Product description

Hypax 1409 BBS is a barium salt of an oxidised wax. This product can be used as a base in water displacing and acid fume resistant anticorrosive films. It has good low temperature adhesion and penetration with self-healing properties and is also non-staining.

Typical analysis

Property	Test	Units	Typical Analysis
Appearance	Visual		Brown paste/grease
Drop point	ASTM-D127	°C	35-46
Barium Content	By calculation	%	2.6%
Acid Value	ASTM D 974	mg KOH/g	28
SAP Value	ASTM D 94	mg KOH/g	92

Application

Hypax 1409 BBS is usually blended further with waxes or oils to alter film hardness, or butyl oxitol at 1-2% to improve water displacing properties. It can be diluted with either oil or solvent depending on the customers requirement for application by brushing, dipping or spraying.

Packaging

Hypax 1409 BBS is available in 170 Kg steel drums and 1000 litre IBCs or as required by the customer. The recommended shelf life of this product is 2 years.

Fulbeck Limited, Fulbeck Road, Newton Aycliffe. DL5 6TX. UK
Tel 0044 (0) 1325 314848. Fax 0044 (0) 1325 314969. admin@fulbeck.uk.com

This information is supplied in good faith to assist customers to assess the applicability of the material in their own products. No warranties are implied or given. ES070819